

## SLOVENSKI STANDARD SIST EN 16682:2017

01-maj-2017

Ohranjanje kulturne dediščine - Navodilo za merjenje vsebnosti vlage v materialih sestavov premične in nepremične kulturne dediščine

Conservation of Cultural Heritage - Guide to the measurements of moisture content in materials constituting movable and immovable cultural heritage

Erhaltung des kulturellen Erbes - Leitfaden zu Messungen des Feuchtegehalts in Materialien des beweglichen und unbeweglichen kulturellen Erbes

(standards.iteh.ai)
Conservation du patrimoine culturel - Guide relatif aux mesures de la teneur en eau de matériaux constituant un patrimoine culturel matériel et immatériel

https://standards.iteh.ai/catalog/standards/sist/98d1e8cc-f333-4607-b848-

Ta slovenski standard je istoveten z: EN 16682:2017

ICS:

97.195 Umetniški in obrtniški izdelki. Items of art and handicrafts.

Kulturne dobrine in kulturna Cultural property and

dediščina heritage

SIST EN 16682:2017 en,fr,de

**SIST EN 16682:2017** 

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 16682:2017

https://standards.iteh.ai/catalog/standards/sist/98d1e8cc-f333-4607-b848-4332c9080a4b/sist-en-16682-2017

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM EN 16682

March 2017

ICS 97.195

#### **English Version**

# Conservation of cultural heritage - Methods of measurement of moisture content, or water content, in materials constituting immovable cultural heritage

Conservation du patrimoine culturel - Méthodes de mesurage de la teneur en humidité, ou teneur en eau, de matériaux constituant un patrimoine culturel immatériel Erhaltung des kulturellen Erbes - Verfahren zur Bestimmung des Feuchte- bzw. Wassergehalts in Materialien des unbeweglichen kulturellen Erbes

This European Standard was approved by CEN on 25 December 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Com	tents	Page
Europ	ean foreword	5
Introd	luction	6
1	Scope	7
2	Normative references	7
3	Terms and definitions	8
4	Symbols and abbreviations	13
5	Moisture and water content in materials	14
5.1	Moisture content	
5.1.1 5.1.2	General  Dry versus wet mode	
5.1.2 5.1.3	Gravimetric versus volumetric mode	
5.2	Water content	
5.3	Comparison between moisture content and water content	15
6	Absolute and relative methods	16
6.1	Absolute methods iTch STANDARD PREVIEW	16
6.2 6.3	Relative methodsComparison between absolute and relative methods 1.21.	10 17
7	Taking and handling samplesSIST EN 16682:2017	
8	SIST EN 16682:2017  Calibration	10
o 8.1	General 4332c9080a4b/sist-en-16682-2017	
8.2	Instrument calibration	19
8.2.1	General	
8.2.2 8.2.3	Calibration for moisture content  Calibration for water content	
8.3	Reproducibility	
8.3.1	Instruments for absolute measurements	19
8.3.2	Instruments for relative measurements	
8.3.3	Comparison between absolute and relative methods	
9	Use of existing European Standards concerning modern building materials	
10	Test report	
Annex	x A (normative) Absolute methods	
<b>A.1</b>	Generalities	
<b>A.2</b>	Gravimetric method	
A.2.1	General	
A.2.2	Apparatus	
A.2.3	Procedure	
<b>A.3</b>	Drying procedures in the gravimetric method	
A.3.1	General	<b>2</b> 3

A.3.2 Oven drying	<b>2</b> 4
A.3.2.1 General	24
A.3.2.2 Apparatus	24
A.3.2.3 Drying procedure	24
A.3.3 Vacuum drying	25
A.3.3.1 General	25
A.3.3.2 Apparatus	25
A.3.3.3 Drying procedure	25
A.3.4 Compressed-air drying	25
A.3.4.1 General	25
A.3.4.2 Apparatus	25
A.3.4.3 Drying procedure	26
A.3.5 Adsorption drying	26
A.3.5.1 General	26
A.3.5.2 Apparatus	26
A.3.5.3 Drying procedure	26
A.3.5.3 Drying procedure  IT en STANDARD PREVIEW  A.3.6 Thermo-gravimetric analysis (TGA)  (standards.iteh.ai)	27
A.3.6.1 General (Standards.iten.al)	27
A.3.6.2 Apparatussistem-166822017	
<b>A.3.6.3 Procedure</b> https://standards.iteh.ai/catalog/standards/sist/98d1e8cc-f333-4607-b844332c9080a4b/sist-en-16682-2017	27
A.4 Karl Fischer titration	28
A.4.1 General	28
A.4.2 Apparatus	28
A.4.3 Procedure	29
A.4.4 Volumetric KF titration (V-KFT)	30
A.4.4.1 General	30
A.4.4.2 Apparatus	30
A.4.4.3 Procedure	30
A.4.5 Coulometric KF titration (C-KFT)	31
A.4.5.1 General	31
A.4.5.2 Apparatus	31
A.4.5.3 Procedure	31
A.4.6 Oven-vaporization KF titration (OV-KFT)	32
A.4.6.1 General	32
A.4.6.2 Apparatus	32
A.4.6.3 Temperature	32

A.4.7	KF titration of selected materials	33
<b>A.5</b>	Azeotropic distillation	34
A.5.1	General	34
A.5.2	Apparatus	34
A.5.3	Procedure	35
<b>A.6</b>	Calcium carbide test	35
A.6.1	General	35
A.6.2	Apparatus	36
A.6.3	Procedure	36
Annex	x B (normative) Relative methods	41
<b>B.1</b>	Generalities	41
<b>B.2</b>	Electrical resistance (conductance)	41
<b>B.3</b>	Capacitance (dielectric)	42
<b>B.4</b>	Relative humidity in equilibrium with the material	43
<b>B.4.1</b>	General	43
<b>B.4.2</b>	Drilled cavity	43
<b>B.4.3</b>	External sealed box (ESB)	44
<b>B.4.4</b>	Apparatus (standards.iteh.ai)	44
B.4.5	Procedure <u>SIST EN 16682 2017</u>	44
Annex	k C (informative) Other relative the air at the standards sist/98d1e8cc-f333-4607-b848-4332c9080a4b/sist-en-16682-2017	49
<b>C.1</b>	Generalities	49
<b>C.2</b>	Microwave	49
<b>C.3</b>	Evanescent-field dielectrometry	50
<b>C.4</b>	Time-domain reflectometry	50
<b>C.5</b>	Nuclear magnetic resonance	51
<b>C.6</b>	Near-infrared spectroscopy (NIRS)	51
<b>C.7</b>	Ultrasound pulses	52
<b>C.8</b>	Thermography	52
Annex	x D (informative) Methods with special safety requirements	57
D.1	Generalities	57
<b>D.2</b>	X-ray	57
<b>D.3</b>	Gamma rays	58
<b>D.4</b>	Neutron scattering	58
Biblio	graphy	61

## **European foreword**

This document (EN 16682:2017) has been prepared by Technical Committee CEN/TC 346 "Conservation of Cultural Heritage", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2017, and conflicting national standards shall be withdrawn at the latest by September 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 16682:2017</u> https://standards.iteh.ai/catalog/standards/sist/98d1e8cc-f333-4607-b848-4332c9080a4b/sist-en-16682-2017

#### Introduction

The specific field of cultural heritage is characterized by particular needs and in most cases the existing standards devised for normal materials cannot be applied. The moisture content, or the water content, in materials is of primary relevance for the preservation of cultural heritage. High content can be very damaging (e.g. salt dissolution and mobilization, fungal infestation, corrosion, swelling) as well as low content (e.g. salt crystallization, shrinkage, wood cracking) or alternating high/low content. It is therefore important to determine and control this variable to assess the risk of damage and take preventive conservation measures.

Different methods exist to measure moisture content, or water content, in modern building materials, based on different physical or chemical principles but most of them are not applicable to cultural heritage and need to be adapted to this aim.

Generally, non-destructive methods are recommended but their accuracy may be limited. In turn, the most accurate methods require sampling and can only exceptionally be used. Readings taken with non-destructive methods may not be comparable especially because they are expressed in different units. The interpretation of measurements may be obscured by a number of factors (e.g. material, salts, temperature) to which the methods are subject.

This European Standard considers and specifies characteristics, operative methodologies, pros and cons of all methods of measurements and establishes a uniform presentation of data and units. It is addressed to anyone who needs to measure or interpret readings of moisture content, or water content, in building materials (particularly masonry and wood), and in general to whoever is responsible for the preservation and maintenance of heritage buildings.

(standards.iteh.ai)

<u>SIST EN 16682:2017</u> https://standards.iteh.ai/catalog/standards/sist/98d1e8cc-f333-4607-b848-4332c9080a4b/sist-en-16682-2017

#### 1 Scope

This European Standard is aimed to inform and assist users in the choice and use of the most appropriate method to obtain reliable measurements of the moisture content, or water content, in wood and masonry (including brickwork, stonework, concrete, gypsum, mortars, etc.) in the specific case of the built cultural heritage.

It provides a basic framework to take and interpret this kind of measurements on the above cultural heritage materials that have undergone weathering, pest attack, salt migration or other transformations over time.

It specifies four absolute methods (i.e. gravimetric, Karl Fischer titration, azeotropic distillation and calcium carbide); explains their characteristics, pros and cons, and gives specifications for the transformation of readings into the same unit to make measurements taken with different methods comparable.

It specifies the three principal relative methods (i.e. electrical resistance, capacitance, and relative humidity in equilibrium with the material), pointing out their characteristics and uncertainties when used in the field of cultural heritage.

In addition, it provides an informative overview of ten other relative methods, their characteristics, pros and cons.

It gives specifications for the calibration of the various methods. It also compares the above methods in relation to their accuracy, sampling requirement, sample size, laboratory or field use, and other problems encountered in the field of cultural heritage to prevent instrument misuse, reduce uncertainties and avoid reading misinterpretation.

#### 2 Normative references

#### SIST EN 16682:2017

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 374-1, Protective gloves against chemicals and micro-organisms - Part 1: Terminology and performance requirements

EN 420:2003+A1:2009, Protective gloves - General requirements and test methods

EN 455-1:2000, Medical gloves for single use - Part 1: Requirements and testing for freedom from holes

EN 772-10:1999, Methods of test for masonry units - Part 10: Determination of moisture content of calcium silicate and autoclaved aerated concrete units

EN 837-1:1996, Pressure gauges - Part 1: Bourdon tube pressure gauges - Dimensions, metrology, requirements and testing

EN 1428:2012, Bitumen and bituminous binders - Determination of water content in bituminous emulsions - Azeotropic distillation method

EN 13183-1:2002, Moisture content of a piece of sawn timber - Part 1: Determination by oven dry method

EN 13183-2:2002, Moisture content of a piece of sawn timber - Part 2: Estimation by electrical resistance method

EN 13183-3:2005, Moisture content of a piece of sawn timber - Part 3: Estimation by capacitance method

EN 15758:2010, Conservation of Cultural Property - Procedures and instruments for measuring temperatures of the air and the surfaces of objects

EN 15898:2011, Conservation of cultural property - Main general terms and definitions

EN 16085:2012, Conservation of Cultural property - Methodology for sampling from materials of cultural property - General rules

EN 16096:2012, Conservation of cultural property - Condition survey and report of built cultural heritage

EN 16242:2012, Conservation of cultural heritage - Procedures and instruments for measuring humidity in the air and moisture exchanges between air and cultural property

EN ISO 10304-1:2009, Water quality - Determination of dissolved anions by liquid chromatography of ions - Part 1: Determination of bromide, chloride, fluoride, nitrate, nitrite, phosphate and sulfate (ISO 10304-1:2007)

EN ISO 11461:2014, Soil quality - Determination of soil water content as a volume fraction using coring sleeves - Gravimetric method (ISO 11461:2001)

EN ISO 13130:2011, Laboratory glassware - Desiccators (ISO 13130:2011)

EN ISO 14911:1999, Water quality - Determination of dissolved Li+, Na+, NH4+, K+, Mn2+, Ca2+, Mg2+, Sr2+ and Ba2+ using ion chromatography - Method for water and waste water (ISO 14911:1998)

EN ISO 15512, Plastics - Determination of water content (ISO 15512)

ISO 760:1978, Determination of water — Karl Fischer method (General method)

https://standards.iteh.ai/catalog/standards/sist/98d1e8cc-f333-4607-b848-

ISO 3567:2011, Vacuum gauges — Calibration by direct comparison with a reference gauge

ISO 5272:1979, Toluene for industrial use — Specifications

ISO 5280:1979, Xylene for industrial use — Specification

ISO 7183:2007, Compressed-air dryers — Specifications and testing

ISO 11465:1993, Soil quality — Determination of dry matter and water content on a mass basis — Gravimetric method

ISO 16979:2003, Wood-based panels — Determination of moisture content

ISO Guide 34:2009, General requirements for the competence of reference material producers

ISO/IEC Guide 98-3:2008, *Uncertainty of measurement* — *Part 3: Guide to the expression of uncertainty in measurement (GUM:1995)* 

EN ISO/IEC 17025:2005, General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025:2005)

#### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 15898:2011 and the following apply.

#### 3.1

#### absolute method/measurement

measuring method whose readings can be expressed in terms of SI units

#### 3.2

#### active sensor

sensor that needs some electrical power supply to operate

#### 3.3

#### atmospheric pressure

#### barometric pressure

pressure is the force per unit area exerted by the air column above the measuring point

Note 1 to entry: This is expressed in hPa (hectopascal).

[SOURCE: EN 16242:2012, 3.2]

#### 3.4

#### bound water

in masonry: water molecules physically or chemically bound to the material; bound water cannot dissolve soluble substances. In wood: water bonded in the cell walls; it is responsible for shrinkage/swelling

## 3.5 iTeh STANDARD PREVIEW

#### crystallization water

## hydration water

## (standards.iteh.ai)

water molecules that are part of a hydrated crystal or molecule

SIST EN 16682:2017

3.6 https://standards.iteh.ai/catalog/standards/sist/98d1e8cc-f333-4607-b848-

#### desiccator

4332c9080a4b/sist-en-16682-2017

equipment in which a desiccant is used to maintain the air as close as possible to the absolutely dry condition

[SOURCE: EN 322:1993, 4.3]

#### 3.7

#### desiccant drying

method in which drying is obtained with a continuous flow of dry air (from compressed air), or with moisture absorption from a highly hygroscopic substance used as desiccant

[SOURCE: EN 322:1993, 4.3]

#### 3.8

#### destructive

causing destruction or damage to cultural heritage materials

#### 3.9

#### dew-point hygrometer

instrument for measuring the temperature at which a cooled parcel of air becomes saturated with water vapour

[SOURCE: EN 16242:2012, 3.4]

#### 3.10

#### dew-point temperature

temperature to which air is cooled at constant pressure and constant water vapour content in order for saturation to occur

Note 1 to entry: This is expressed in degrees Celsius (°C).

[SOURCE: EN 15758:2010, 3.6]

#### 3.11

### dry air

atmospheric air without water vapour

[SOURCE: EN 16242:2012, 3.6]

#### 3.12

#### dry matter

whole of the substances which do not volatilize under the conditions of drying specified in this standard

[SOURCE: ISO 1026:1982, 2.1]

#### 3.13

#### equilibrium moisture content

## iTeh STANDARD PREVIEW

moisture content at which a material neither loses nor gains moisture from the surrounding atmosphere at given relative humidity and temperature levels equal (

Note 1 to entry: This is expressed in g/kg as the ratio of the mass of the same material. https://standards.iteh.ai/catalog/standards/sist/98d1e8cc-f333-4607-b848-

4332c9080a4b/sist-en-16682-2017

[SOURCE: EN 16242:2012, 3.8]

#### 3.14

#### external sealed box

#### **ESB**

box with five thermally insulating and impermeable faces and one missing face, fixed to the surface of a material to create an air pocket in hygrometric equilibrium with the material

#### 3.15

#### fibre saturation point

moisture content at which no free water is present in wood, while the cell walls are saturated with bound water

#### 3.16

#### free water

in masonry: liquid water inside pores. In wood: water contained in the cell cavities. It can dissolve soluble substances

#### 3.17

#### hygrometer

instrument measuring relative humidity

Note 1 to entry: It generally comprises a sensor, which is set in equilibrium with the air, and a system that transforms the signal from the sensor into humidity readings.

[SOURCE: EN 16242:2012, 3.11]

#### 3.18

#### invasive

requiring the entry of a probe, or other instrument into a cultural heritage material, for diagnostic purposes

#### 3.19

#### irreversible relative humidity sensor

sensor in which reached relative humidity levels remain permanently marked

#### 3.20

#### minimally destructive

#### minimally invasive

damage caused, or the sample taken, are very small and not easily recognizable, so that it can be considered acceptable, or justified in view of the advantages expected from the analysis

## iTeh STANDARD PREVIEW

#### 3.21

#### moisture content

(standards.iteh.ai)

MC

amount of water in the material, as determined in accordance with a gravimetric method specified in this European Standard, the method may include the volatile organic compounds that may be lost when the material is heated at moderate temperaturest-en-16682-2017

Note 1 to entry: The MC is expressed as a mass fraction in percent (%).

#### 3.22

#### oven drying

drying method obtained with a ventilated oven at temperature 103°C ± 2°C

[SOURCE: EN 322:1993, 4.2]

#### 3.23

#### passive sensor

sensor that does not need any electrical power supply to operate

#### 3.24

#### proxy

material or a specimen that is a substitute or a replacement for something else, under the assumption of identical behaviour of the material under investigation

#### 3.25

#### relative humidity

#### RH

ratio of the actual vapour pressure of the air to the saturation vapour pressure

Note 1 to entry: The RH is expressed in percent (%).

[SOURCE: EN 15757:2010, 3.9]

#### 3.26

#### relative method

#### relative measurement

measuring method whose readings cannot be expressed in terms of SI units and should be expressed in relation to something else, kept as a reference

Note 1 to entry: The scale depends on the specific choice of the reference; it can also be expressed as a fraction of a given value.

#### 3.27

#### sample

portion of material, ideally representative, removed from the cultural property for scientific investigation

## [SOURCE: EN 16085:2012, 3.2] Teh STANDARD PREVIEW

## 3.28

temperature

(standards.iteh.ai)

temperature read on a thermometer which is  $\underbrace{\text{exposed}_{6822171}\text{in}}_{\text{radiation or other energy sources}}$  and  $\underbrace{\text{exposed}_{6822171}\text{in}}_{\text{catalog/standards/sist/98d1e8cc-f333-4607-b848-}}$ 

4332c9080a4b/sist-en-16682-2017

Note 1 to entry: The temperature is expressed in degrees Celsius (°C).

[SOURCE: EN 15758:2010, 3.1]

#### 3.29

#### thermometer

instrument to measure temperature which comprises a sensor which is placed in thermal equilibrium with the air (if it measures the air temperature) or the surface, sometimes a probe that contains and protects the sensor, and a system that transforms the input from the sensor into an output expressed in degrees Celsius (°C)

[SOURCE: EN 15758:2010, 3.20]

#### 3.30

#### vacuum drying

drying method obtained by vacuum pumping to lower the atmospheric pressure to  $4 \pm 2$  hPa in the drying chamber

#### 3.31

## vacuum gauge

instrument for measuring gas or vapour pressures that are less than the prevailing atmospheric pressure

[SOURCE: ISO 3529-3:2014, 2.1.2]

#### 3.32

#### water content

#### WC

amount of water in the material, as determined in accordance with the Karl Fisher titration specified in this European Standard; this method may include crystallization water

Note 1 to entry: The WC is expressed as a mass fraction in percent (%).

## Symbols and abbreviations

**EFD Evanescent-Field Dielectrometry** 

**EMC Equilibrium Moisture Content** 

**ESB External Sealed Box** 

International Atomic Energy Agency, Vienna **IAEA** 

Karl Fischer KF

**KFT** Karl Fischer titration

C-KFT coulometric KFT V-KFT volumetric KFT

Moisture Content expressed on dry basis MC

Moisture Content expressed on wet basis  $MC_{\rm w}$ 

(standards.iteh.ai) **Near Infrared** NIR

Near Infrared Spectroscopy<sub>T EN 16682:2017</sub> **NIRS** 

Nuclear Magnetici Resignance standards/sist/98d1e8cc-f333-4607-b848-**NMR** 

Oven-vaporization KF titration 4332c9080a4b/sist-en-16682-2017 **OV-KFT** 

C-OV-KFT coulometric oven-vaporization KF titration V-OV-KFT volumetric oven-vaporization KF titration

RH **Relative Humidity** 

SI units International System of units

**SRXTM** Synchrotron-based X-ray Tomographic Microscopy

TDR Time-Domain Reflectometry **TGA** Thermogravimetric Analysis VOC volatile organic compounds

WC Water content expressed on dry basis  $WC_w$ Water content expressed on wet basis

dielectric constant 3

initial (moist) mass of the test sample  $m_H$ 

mass of the sample after drying  $m_0$ 

mass of water extracted from the sample  $m_w$