

SLOVENSKI STANDARD

SIST EN ISO 17636-2:2023

01-marec-2023

Nadomešča:

SIST EN ISO 17636-2:2013

**Neporušitveno preskušanje zvarnih spojev - Radiografsko preskušanje - 2. del:
Tehnike z rentgenskimi in gama žarki z uporabo digitalnih detektorjev (ISO 17636-2:2022)**

Non-destructive testing of welds - Radiographic testing - Part 2: X- and gamma-ray techniques with digital detectors (ISO 17636-2:2022)

Zerstörungsfreie Prüfung von Schweißverbindungen - Durchstrahlungsprüfung - Teil 2: Röntgen- und Gammastrahlungstechniken mit digitalen Detektoren (ISO 17636-2:2022)

Essais non destructifs des assemblages soudés - Contrôle par radiographie - Partie 2: Techniques par rayons X ou gamma à l'aide de détecteurs numériques (ISO 17636-2:2022)

Ta slovenski standard je istoveten z: EN ISO 17636-2:2022

ICS:

25.160.40

Varjeni spoji in vari

Welded joints and welds

SIST EN ISO 17636-2:2023

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 17636-2

October 2022

ICS 25.160.40

Supersedes EN ISO 17636-2:2013

English Version

**Non-destructive testing of welds - Radiographic testing -
Part 2: X- and gamma-ray techniques with digital detectors
(ISO 17636-2:2022)**

Essais non destructifs des assemblages soudés -
Contrôle par radiographie - Partie 2: Techniques par
rayons X ou gamma à l'aide de détecteurs numériques
(ISO 17636-2:2022)

Zerstörungsfreie Prüfung von Schweißverbindungen -
Durchstrahlungsprüfung - Teil 2: Röntgen- und
Gammastrahlungstechniken mit digitalen Detektoren
(ISO 17636-2:2022)

This European Standard was approved by CEN on 23 August 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

| | |
|------------------------|---|
| European foreword..... | 3 |
|------------------------|---|

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 17636-2:2023

<https://standards.iteh.ai/catalog/standards/sist/9ae4d2ea-6aa2-4768-8c06-34a58c9b3910/sist-en-iso-17636-2-2023>

European foreword

This document (EN ISO 17636-2:2022) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2023, and conflicting national standards shall be withdrawn at the latest by April 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 17636-2:2013.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 17636-2:2022 has been approved by CEN as EN ISO 17636-2:2022 without any modification.

INTERNATIONAL STANDARD

ISO
17636-2

Second edition
2022-09

Non-destructive testing of welds — Radiographic testing —

Part 2: X- and gamma-ray techniques with digital detectors

iTeh STANDARD PREVIEW
(standards.iteh.ai)

*Essais non destructifs des assemblages soudés — Contrôle par
radiographie —*

*Partie 2: Techniques par rayons X ou gamma à l'aide de détecteurs
numériques*

SIST EN ISO 17636-2:2023

<https://standards.iteh.ai/catalog/standards/sist/9ae4d2ea-6aa2-4768-8c06-34a58e9b3910/sist-en-iso-17636-2-2023>



Reference number
ISO 17636-2:2022(E)

© ISO 2022

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 17636-2:2023

<https://standards.iteh.ai/catalog/standards/sist/9ae4d2ea-6aa2-4768-8c06-34a58e9b3910/sist-en-iso-17636-2-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

| | |
|---|-----------|
| Foreword | v |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions | 2 |
| 4 Symbols and abbreviated terms | 6 |
| 5 Classification of radiographic techniques and compensation principles | 8 |
| 5.1 Classification | 8 |
| 5.2 Compensation principles, CP I, CP II or CP III | 8 |
| 5.2.1 General | 8 |
| 5.2.2 Compensation principle I (CP I) | 8 |
| 5.2.3 Compensation principle II (CP II) | 8 |
| 5.2.4 Compensation principle III (CP III) | 8 |
| 5.2.5 Theoretical background | 9 |
| 6 General preparations and requirements | 9 |
| 6.1 Protection against ionizing radiation | 9 |
| 6.2 Surface preparation and stage of manufacture | 9 |
| 6.3 Location of the weld in the radiograph | 9 |
| 6.4 Identification of radiographs | 9 |
| 6.5 Marking | 9 |
| 6.6 Overlap of digital images | 10 |
| 6.7 Types and positions of image quality indicators (IQIs) | 10 |
| 6.7.1 General | 10 |
| 6.7.2 Duplex wire IQIs | 10 |
| 6.7.3 Single wire or step-hole IQIs | 10 |
| 6.8 Evaluation of image quality | 11 |
| 6.9 Minimum image quality values | 12 |
| 6.10 Personnel qualification | 12 |
| 7 Recommended techniques | 13 |
| 7.1 Test arrangements | 13 |
| 7.1.1 General | 13 |
| 7.1.2 Single-wall penetration of plane objects (see Figure 1) | 14 |
| 7.1.3 Single-wall penetration of curved objects with the source outside the object (see Figures 2 to 4) | 14 |
| 7.1.4 Single-wall penetration of curved objects with the source inside the object for panoramic exposure (see Figures 5 to 7) | 15 |
| 7.1.5 Single-wall penetration of curved objects with the source located off-centre and inside the object (see Figures 8 to 10) | 16 |
| 7.1.6 Double-wall penetration and double-image evaluation (DWDI) of pipes with the elliptic technique and the source and the detector outside the object (see Figure 11) | 17 |
| 7.1.7 Double-wall penetration and double-image evaluation (DWDI) with the perpendicular technique and source and detector outside the object (see Figure 12) | 17 |
| 7.1.8 Double-wall penetration and single-image evaluation (DWSI) of curved objects for evaluation of the wall next to the detector (see Figures 13 to 16) | 18 |
| 7.1.9 Penetration of objects with different material thicknesses (see Figure 17 to 19) | 19 |
| 7.2 Choice of tube voltage and radiation source | 20 |
| 7.2.1 X-ray devices up to 1 000 kV | 20 |
| 7.2.2 Other radiation sources | 21 |
| 7.3 Detector systems and metal screens | 22 |
| 7.3.1 Minimum normalized signal-to-noise ratio (SNR_N) | 22 |

ISO 17636-2:2022(E)

| | | |
|------------------------------|---|-----------|
| 7.3.2 | Compensation principle II..... | 25 |
| 7.3.3 | Metal screens for IPs and shielding..... | 25 |
| 7.4 | Alignment of beam..... | 25 |
| 7.5 | Reduction of scattered radiation..... | 26 |
| 7.5.1 | Metal filters and collimators..... | 26 |
| 7.5.2 | Interception of backscattered radiation..... | 26 |
| 7.6 | Source-to-object distance..... | 26 |
| 7.7 | Geometric magnification technique..... | 33 |
| 7.8 | Maximum area for a single exposure..... | 34 |
| 7.9 | Processing..... | 34 |
| 7.9.1 | Scan and read-out of images..... | 34 |
| 7.9.2 | Correction of acquired DDA images..... | 35 |
| 7.9.3 | Bad pixel interpolation..... | 35 |
| 7.9.4 | Image processing..... | 35 |
| 7.10 | Monitor viewing conditions and storage of digital radiographs..... | 36 |
| 8 | Test report..... | 36 |
| Annex A (normative) | Number of exposures for acceptable testing of a circumferential butt weld..... | 38 |
| Annex B (normative) | Minimum image quality values..... | 43 |
| Annex C (normative) | Determination of basic spatial resolution..... | 51 |
| Annex D (informative) | Determination of minimum grey values for CR practice..... | 53 |
| Annex E (informative) | Grey values — General remarks..... | 58 |
| Annex F (informative) | Considering the detector unsharpness for f_{\min}..... | 60 |
| Annex G (informative) | Calculation of recommended X-ray tube voltages from Figure 20..... | 63 |
| Bibliography | | 64 |

SIST EN ISO 17636-2:2023

<https://standards.iteh.ai/catalog/standards/sist/9ae4d2ea-6aa2-4768-8c06-34a58e9b3910/sist-en-iso-17636-2-2023>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 17636-2:2013), which has been technically revised.

The main changes are as follows:

- the normative references have been updated;
- the figures have been updated;
- manual and automated inspection with DDAs has been considered in [6.6](#), [6.7](#), and [7.8](#);
- references to [Figures 1](#) to [19](#) have been updated throughout the document;
- in [6.7 a\)](#), the acceptance of a wire visibility shorter than 10 mm for pipes with an external diameter < 50 mm has been added;
- in [6.7.1](#), the use of ASTM wires and other IQIs by agreement of the contracting parties has been added;
- [6.8](#), “Evaluation of image quality” for digital radiography has been added;
- in [6.9](#) and [7.2.2](#), the lower thickness limit for Se-75 applications has been deleted;
- in [6.8](#), [6.9](#) and [7.3.1](#), a clarification for the IQI usage for DWDI technique has been added;
- permission to reduce SNR_N if the tube voltage is reduced or energy-resolving detectors are used to < 80 % of the values given in [Figure 20](#) has been added in [7.3.1](#);

ISO 17636-2:2022(E)

- in [7.3.2](#), the compensation principle II (CP II) has been extended to three wire pairs without the agreement of the contracting parties;
- [Annex C](#) has been shortened to avoid duplication with ISO 19232-5;
- in [D.2](#), a new note on fading has been added;
- a new [Annex F](#) has been added;
- a new [Annex G](#) has been added.

A list of all parts in the ISO 17636 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html. Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 17636-2:2023

<https://standards.iteh.ai/catalog/standards/sist/9ae4d2ea-6aa2-4768-8c06-34a58e9b3910/sist-en-iso-17636-2-2023>

Non-destructive testing of welds — Radiographic testing —

Part 2: X- and gamma-ray techniques with digital detectors

1 Scope

This document specifies techniques of digital radiography with the object of enabling satisfactory and repeatable results. The techniques are based on generally recognized practice and fundamental theory of the subject.

This document applies to the digital radiographic testing of fusion welded joints in metallic materials. It applies to the joints of plates and pipes. Besides its conventional meaning, “pipe”, as used in this document, covers other cylindrical bodies such as tubes, penstocks, boiler drums and pressure vessels.

This document specifies the requirements for digital radiographic X- and gamma-ray testing by either computed radiography (CR) or radiography with digital detector arrays (DDAs) of the welded joints of metallic plates and tubes for the detection of imperfections. It includes manual and automated inspection with DDAs.

Digital detectors provide a digital grey value image which can be viewed and evaluated using a computer ([Annex E](#)). This document specifies the recommended procedure for detector selection and radiographic practice. Selection of computer, software, monitor, printer and viewing conditions are important, but are not the main focus of this document. The procedure specified in this document provides the minimum requirements for radiographic practice which permits exposure and acquisition of digital radiographs with equivalent sensitivity for the detection of imperfections as film radiography (specified in ISO 17636-1).

This document does not specify acceptance levels for any of the indications found on the digital radiographs. ISO 10675 provides information on acceptance levels for weld inspection.

If contracting parties apply lower test criteria, it is possible that the quality achieved will be significantly lower than when this document is strictly applied.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5576, *Non-destructive testing — Industrial X-ray and gamma-ray radiology — Vocabulary*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 16371-1:2011, *Non-destructive testing — Industrial computed radiography with storage phosphor imaging plates — Part 1: Classification of systems*

ISO 19232-1, *Non-destructive testing — Image quality of radiographs — Part 1: Determination of the image quality value using wire-type image quality indicators*

ISO 19232-2, *Non-destructive testing — Image quality of radiographs — Part 2: Determination of the image quality value using step/hole-type image quality indicators*

ISO 19232-4, *Non-destructive testing — Image quality of radiographs — Part 4: Experimental evaluation of image quality values and image quality tables*

ISO 17636-2:2022(E)

ISO 19232-5, *Non-destructive testing — Image quality of radiographs — Part 5: Determination of the image unsharpness and basic spatial resolution value using duplex wire-type image quality indicators*

EN 12543 (all parts), *Non-destructive testing — Characteristics of focal spots in industrial X-ray systems for use in non-destructive testing*

EN 12679, *Non-destructive testing — Radiographic testing — Determination of the size of industrial radiographic gamma sources*

ASTM E747, *Standard Practice for Design, Manufacture and Material Grouping Classification of Wire Image Quality Indicators (IQI) Used for Radiology*

JIS Z2306, *Radiographic image quality indicators for non-destructive testing*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 5576 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 computed radiography CR

complete system comprising a *storage phosphor imaging plate* (IP) (3.2) and a corresponding read-out unit (scanner or reader), which converts the information from the IP into a digital image

3.2 storage phosphor imaging plate IP

photostimulable luminescent material capable of storing a latent radiographic image of a material being tested and which, upon stimulation by a source of red light of appropriate wavelength, generates luminescence proportional to radiation absorbed

Note 1 to entry: When performing *computed radiography* (3.1), an IP is used in lieu of a film. When establishing techniques related to *source size* (3.20) or focal geometries, the IP is referred to as a detector, i.e. *source-to-detector distance* (3.21).

3.3 digital detector array DDA

electronic device converting ionizing or penetrating radiation into a discrete array of analogue signals which are subsequently digitized and transferred to a computer for display as a digital image corresponding to the radiologic energy pattern imparted upon the input region of the device

3.4 structure noise

<imaging plate> local sensitivity variations due to inhomogeneities in the sensitive layer (structure, graininess) and surface of an imaging plate

Note 1 to entry: After scanning of the exposed imaging plate, the inhomogeneities appear as overlaid fixed pattern noise in the digital image.

Note 2 to entry: This noise limits the maximum achievable image quality of digital CR images and can be compared with the graininess in film images.

3.5

structure noise

<digital detector array> local sensitivity variations due to different properties of detector elements (pixels)

Note 1 to entry: After read-out of the exposed uncorrected *digital detector array* (DDA) (3.3) image, the inhomogeneities of the DDA appear as overlaid fixed pattern noise in the digital image. Therefore, all DDAs require, after read-out, a software-based image correction (software and guidelines are provided by the manufacturer). A suitable correction procedure reduces the structure noise.

Note 2 to entry: The image correction is also called “calibration” in other documents.

3.6

grey value

GV

numeric value of a pixel in a digital image

Note 1 to entry: This is typically interchangeable with the terms “pixel value”, “detector response”, “analogue-to-digital unit” and “detector signal”.

Note 2 to entry: For further information, see [Annex E](#).

3.7

linearized grey value

numeric value of a pixel which is directly proportional to the detector exposure dose, having a value of zero if the detector was not exposed

Note 1 to entry: This is typically interchangeable with the terms “linearized pixel value” and “linearized detector signal”.

3.8

basic spatial resolution of a digital detector

$SR_{b, \text{detector}}$

half of the measured detector unsharpness in a digital image, which corresponds to the effective pixel size and indicates the smallest geometrical detail which can be resolved with a digital detector at magnification equal to one

Note 1 to entry: For this measurement, the duplex wire IQI is placed directly on the *digital detector array* (3.3) or imaging plate.

Note 2 to entry: The measurement of unsharpness is described in ISO 19232-5. See also ASTM E1000 and ASTM E2736.

3.9

basic spatial resolution of a digital image

$SR_{b, \text{image}}$

half of the measured image unsharpness in a digital image, which corresponds to the effective pixel size and indicates the smallest geometrical detail which can be resolved in a digital image

Note 1 to entry: For this measurement, the duplex wire IQI is placed directly on the object (source side).

Note 2 to entry: The measurement of unsharpness is described in ISO 19232-5. See also ASTM E1000 and ASTM E2736.

3.10

signal-to-noise ratio

SNR

ratio of mean value of the *linearized grey values* (3.7) to the standard deviation of the linearized grey values (noise) in a given *region of interest* (3.25) in a digital image